



ARL-TN-0720 • DEC 2015



Synthesis of Al_2O_3 -Coated Fe_3O_4 Nanoparticles for Thermomagnetic Processing

by Victoria L Blair and Joseph Marsico

NOTICES

Disclaimers

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturer's or trade names does not constitute an official endorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.



Synthesis of Al_2O_3 -Coated Fe_3O_4 Nanoparticles for Thermomagnetic Processing

by Victoria L Blair

Weapons and Materials Research Directorate, ARL

by Joseph Marsico

Rochester Institute of Technology, Rochester, NY

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188	
<p>Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to Department of Defense, Washington Headquarters Services, Directorate for Information Operations and Reports (0704-0188), 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302. Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.</p> <p>PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ADDRESS.</p>					
1. REPORT DATE (DD-MM-YYYY) December 2015		2. REPORT TYPE Technical Note		3. DATES COVERED (From - To) 1 June–30 September 2015	
4. TITLE AND SUBTITLE Synthesis of Al ₂ O ₃ -Coated Fe ₃ O ₄ Nanoparticles for Thermomagnetic Processing				5a. CONTRACT NUMBER	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
6. AUTHOR(S) Victoria L Blair and Joseph Marsico				5d. PROJECT NUMBER DSI14-WM-014	
				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) US Army Research Laboratory ATTN: RDRL-WMM-E Aberdeen Proving Ground, MD 21005-5069				8. PERFORMING ORGANIZATION REPORT NUMBER ARL-TN-0720	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)				10. SPONSOR/MONITOR'S ACRONYM(S)	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution is unlimited.					
13. SUPPLEMENTARY NOTES					
14. ABSTRACT Current research at the US Army Research Laboratory (ARL) has been focused on understanding the underlying physics of external fields on materials synthesis and processing, also known as Energy Coupled to Matter. This technical note will describe a combination of synthesis processes by which a new composite material will be produced for future work in thermomagnetic processing at ARL. This novel process will be used to fabricate ceramic parts with tailored physical properties to enable new applications that benefit the Army. Potential applications could include new devices or equipment that enhance the performance of Soldier and vehicle protection systems.					
15. SUBJECT TERMS thermomagnetic processing, nanoparticles, synthesis, core/shell particles, composites					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT UU	18. NUMBER OF PAGES 14	19a. NAME OF RESPONSIBLE PERSON Victoria L Blair
a. REPORT Unclassified	b. ABSTRACT Unclassified	c. THIS PAGE Unclassified			19b. TELEPHONE NUMBER (Include area code) 410-306-4947

Contents

Acknowledgments	iv
1. Introduction	1
2. Synthesis Method	1
3. Conclusion and Future Work	3
4. References	4
List of Symbols, Abbreviations, and Acronyms	6
Distribution List	7

Acknowledgments

Special thanks to the US Army Research Laboratory's Ceramics and Transparent Materials Branch researchers for all their technical guidance.

1. Introduction


Recent work in materials processing and manufacturing research has been focused on using nontraditional parameters to influence the properties of the final parts. This includes the application of high-strength magnetic fields on materials during synthesis, processing, and/or densification. In the case of ceramics, there is significant work being completed on the forming process of alumina under a magnetic field.¹⁻⁶ Most recently by Sakka et al.,^{5,6} researchers were able to develop a highly textured microstructure from both slip casting and gel casting under a magnetic field. The bodies maintained a relatively high degree of texture after sintering despite particle rearrangement during the sintering process.

Oak Ridge National Laboratory has conducted research on the application of high-strength magnetic fields during high-temperature processing for alloy formation. It has been shown through computer simulations that the addition of an approximately 9-T external magnetic field can influence phase development in steel alloys.⁷⁻⁹ Furthermore, additional studies have demonstrated texture development in weakly magnetic metals during sintering under an applied magnetic field.^{1-3,9} Current research within the US Army Research Laboratory has been focused on Energy Coupled to Matter for exploring fundamental physics during processing in external fields to obtain novel materials with tailored properties. One future goal is the development of a core-shell structures in which the magnetic core is responsive under an applied magnetic field and the nonresponsive portion of the shell is the majority phase. A process will be described for producing magnetic magnetite (Fe₃O₄) nanoparticles with a thick shell of alumina to be used during thermomagnetic processing. The process will be inspired by similar procedures described in the literature.¹⁰

2. Synthesis Method

Clean laboratory glassware was required to avoid impurities in the end product. Deionized (DI) water (H₂O) was degassed using house nitrogen (N), allowing for the N to bubble through about 100 mL of H₂O for 10 min before starting synthesis.

A 2:1 ratio of iron Fe³⁺ ions to Fe²⁺ ions from Fe (III) sulfate and Fe (II) chloride was required for the synthesis process. Fe₃O₄ is a ferrite that has both cation valences in the oxide, as demonstrated in the following chemical reaction:



To acquire the correct ratio, it was necessary to know the exact amount of H₂O hydrating the sulfate and the chloride. These data were obtained from thermogravimetric analysis up to a temperature of at least 1,000 °C to enable the formation of iron oxide. The results were used to back-calculate the exact stoichiometry of the precursor materials.

Once the DI H₂O was degassed, it was poured into a sample reaction vessel with the precursor materials. This was an exothermic reaction completed in a fume hood, adding the H₂O slowly. While the mixture was boiling and cooling down, a solution of sodium hydroxide (NaOH) was prepared in DI H₂O and degassed with house N (as described earlier) for a minimum of 60 min. Once the NaOH solution was finished degassing, an Fe/H₂O mixture was slowly added to the NaOH solution while continuing to bubble house N through the system. Keeping oxygen (O) out of the system was necessary to prevent premature oxidation of the Fe cations. After this step, the Fe₃O₄ particles precipitated out of solution, leaving behind H₂O, NaCl, and Na₂SO₄.

Next, the solution was heated at approximately 85 °C and stirred while continuing to bubble N through the suspension. After 3 h, the heat was turned off, allowing the solution to cool while keeping the N bubbling. Once the suspension was cooled, it could be filtered. While filtering, the mother suspension continued to bubble N. The Fe₃O₄ was washed twice in DI H₂O and once in isopropyl alcohol (IPA). Following the IPA rinse, the Fe₃O₄ was heated in a beaker up to 100 °C with N blowing on it so the IPA could evaporate. Once the IPA was evaporated, drying was continued in an oven. The surface area was measured (by N absorption in BET [Brunauer-Emmett-Teller]) on the resulting Fe₃O₄ nanoparticles and found to be 133 m²/g.

An in situ nanoprecipitation process was used to coat the Fe₃O₄ particles with alumina.¹¹ Prior to precipitation, 2 solutions were prepared, including an acidic solution (solution A) and a basic solution (solution B). The acidic solution consisted of aluminum (Al) nitrate, magnesium (Mg) nitrate, and rare earth (RE) nitrate in stoichiometric amounts to acquire a composition of RE_{0.002}Al_{1.998}O₃ with 250 ppm of magnesium oxide. Adding Mg to alumina had the dual purpose of creating structural distortion to assist in dissolving the erbium into the Al octahedral site and behaving as a grain growth inhibitor. DI H₂O was added to the mixed nitrates to acquire a 7.5-M solution of Al(NO₃)₃ (RE and Mg nitrates were not included in the calculation). The basic solution consisted of 11% by weight ammonium bicarbonate and 3% by weight ammonium hydroxide in DI H₂O. Both solutions were stirred until all crystals were dissolved, adding heat when necessary.

Once solutions A and B were prepared, a third solution, referred to as the buffer, was mixed to host the reactions. The amount of buffer solution (2% by weight ammonium bicarbonate in DI H₂O) was dependent on the batch size. The pH of the buffer was adjusted to approximately 7 by adding a small amount of nitric acid. To coat the Fe₃O₄ particles, approximately 1.5-wt% Fe₃O₄ (based on the calculated mass of alumina) was added to the buffer solution and allowed to stir vigorously, keeping the particles suspended. Finally, solutions A and B were added drop-wise to the buffer/Fe₃O₄ suspension such that the pH remained at approximately 7 during the entire precipitation step. When solution A was exhausted, the resulting suspension was allowed to age while stirring vigorously overnight.

The following day, the suspension was filtered from the NaCl solution. The resulting powder was washed twice with DI H₂O and once with IPA. After washing, the powder was placed into an oven to dry. The dry powder was gently crushed and calcined at 1,300 °C for 30 min in air. The final surface area of the calcined composite powder was 7.28 m²/g, which was a significant change from the as-synthesized Fe₃O₄ nanoparticles. It is possible that this was the result of the coating of alumina on the surface reducing the total surface area.

3. Conclusion and Future Work

Fe₃O₄ nanoparticles have been synthesized with high surface area using a mixture of Fe valence cations to precipitate the particles from solution. The particles were confirmed to be magnetite by X-ray diffraction, consistent with the observation of particles sticking to magnetic stir bars. The resulting nanoparticles were coated with alumina by nanoprecipitation onto the particle surface and calcined. The surface area was shown to decrease, likely due to either alumina coating or grain growth of the powders during calcination.

Future work will involve additional characterization of the alumina/Fe₃O₄ composite powder, including detailed X-ray diffraction with a molybdenum X-ray source to limit fluorescence from the Fe in the sample. Microscopy will be conducted to determine if the core/shell structure was obtained, and transmission electron microscopy may be used to observe the bonding between the Fe₃O₄ core and the alumina shell. Once the characterization has been completed, work will begin on the magnetic field processing of this new composite material.

4. References

1. Sun ZHI, Guo M, Vleugels J, Van der Biest O, Blanpain B. Strong static magnetic field processing of metallic materials: a review. *Current Opinion in Solid State and Materials Science*. 2012;16(5):254–267.
2. Sun ZHI, Guo M, Vleugels J, Van der Biest O, Blanpain B. Processing of non-ferromagnetic materials in strong static magnetic field. *Current Opinion in Solid State and Materials Science*. 2013;17(4):193–201.
3. Sun ZHI, Guo X, Guo M, Vleugels J, Van der Biest O, Blanpain B. Alignment of weakly magnetic metals during solidification in a strong magnetic field. *Journal of Alloys and Compounds*. 2013;551:568–577.
4. Sun ZHI, Zhang X, Guo M, Pandelaers L, Vleugels J, Van der Biest O, Van Reusel K, Blanpain B. Strong magnetic field effects on solid-liquid and particle-particle interactions during the processing of a conducting liquid containing non-conducting particles. *Journal of Colloid and Interface Science*. 2012;375:203–212.
5. Szudarska A, Sakka Y, Suzuki TS, Mizerski T, Szafran M. Magnetic field alignment in highly concentrated suspensions for gelcasting process. *Ceramics International*. 2016;42:294–301.
6. Szudarska A, Mizerski T, Sakka Y, Suzuki TS, Szafran M. Fabrication of textured alumina by magnetic alignment via gelcasting based on low-toxic system. *Journal of the European Ceramic Society*. 2014;34(15):3841–3848.
7. Jaramillo RA, Babu SS, Ludtka GM, Kisner RA, Wilgen JB, Mackiewicz-Ludtka G, Nicholson DM, Kelly SM, Murugananth M, Bhadeshia HKDH. Effect of 30T magnetic field on transformations in a novel bainitic steel. *Scripta Materialia*. 2005;52:461–466.
8. Ludtka GM, Jaramillo RA, Kisner RA, Nicholson DM, Wilgen JB, Mackiewicz-Ludtka G, Kalu PN. In situ evidence of enhanced transformation kinetics in a medium carbon steel due to a high magnetic field. *Scripta Materialia*. 2004;51:171–174.
9. Radhakrishnan B, Nicholson DM, Eisenbach M, Parish C, Ludtka GM, Rios O. Alignment of iron nanoparticles in a magnetic field due to shape anisotropy. *Journal of Magnetism and Magnetic Materials*. 2015;394:481–490.
10. Laurent S, Forge D, Port M, Roch A, Robic C, Vander Elst L, Muller RN. Magnetic iron oxide nanoparticles: synthesis, stabilization, vectorization,

Approved for public release; distribution is unlimited.

physicochemical characterizations, and biological applications. Chemical Reviews. 2008;108(6):2064–2110.

11. Sanamyan T, Pavlacka R, Gilde G, Dubinskii M. Spectroscopic properties of Er^{3+} -doped $\alpha\text{-Al}_2\text{O}_3$. Optical Materials. 2013;35:821–826.

List of Symbols, Abbreviations, and Acronyms

Al	aluminum
DI	deionized
Fe ₃ O ₄	magnetite
H ₂ O	water
IPA	isopropyl alcohol
Mg	magnesium
N	nitrogen
NaOH	sodium hydroxide
O	oxygen
RE	rare earth

1 DEFENSE TECHNICAL
(PDF) INFORMATION CTR
DTIC OCA

2 DIRECTOR
(PDF) US ARMY RESEARCH LAB
RDRL CIO LL
IMAL HRA MAIL & RECORDS
MGMT

1 GOVT PRINTG OFC
(PDF) A MALHOTRA

1 DIR USARL
(PDF) RDRL WMM E
VL BLAIR

INTENTIONALLY LEFT BLANK.